

Step 2. Layering

Import the file for the spiral top.

In cura the settings follow as:

250° Nozzle Temp.

35° Bed Temp.

80 mm/s Print Speed

SPIRALIZE

If you do not spiralize the top layer the print will fail

